

Laborsil pro 70



Technical Data Sheet

Product description: Addition-vulcanising kneadable silicone for the universal use in the dental lab with a final hardness of 70 Shore A

Manufacturer: Dreve Dentamid GmbH
Max-Planck-Straße 31
59423 Unna / Germany

Composition:

Pos	chemical term
1	Polyvinylmethylsiloxane
2	Silicic acid
3	Polymethylhydrogensiloxane
4	Platin-catalyst
5	Fillers
5	pigments

Properties:

Colour: light grey

Hardness Shore A: 70 ±2

Processing time: 90sec. ± 15 sec. at 23°C

Demoulding at 23°C: 5:00 min. ± 1:00 min.

Consistency: Type 0: kneadable (ISO 4823)

Recovery from deformation: >99,2 % (ISO 4823)

Deformation under pressure: 3,0 % (ISO 4823)

Linear dimensionel change: < 0,2 % (ISO 4823)

Dreve Dentamid GmbH
Max-Planck-Str. 31
59423 Unna / Germany
Tel.: 02303 / 8807-0
Fax: 02303 / 8807-55
Info@dreve.de
www.dreve.com